



DOWSIL™ 983 Structural Glazing Sealant

Features & Benefits

- Approved for structural applications.¹
- Meets ASTM C1184 Standard Specification for Structural Silicone Sealant.
- Meets ASTM C719 Class 25 Higher movement capability \pm 25%.
- Improved productivity.
- Low VOC formula.

¹All structural applications MUST be reviewed by the technical staff. If their recommendations are followed, Dow will issue a structural adhesive warranty for a specific job.

Composition

- Two-part, neutral-cure, RTV silicone sealant.

Applications

- DOWSIL™ 983 Structural Glazing Sealant is designed for factory glazing and curtain wall production. It is suitable for use where dual structural and weatherseal applications are desired, with up to \pm 25% movement capability in a well-designed weatherseal. Once cured, this structural sealant forms a durable, flexible and watertight bond. It has excellent unprimed adhesion to most glass, chromated and anodized aluminum and many painted aluminum surfaces. DOWSIL™ Primer-C may be required for fast and consistent adhesion to polyester powder coat and fluorocarbon coatings and other high performance coated substrates approved for architectural structural glazing applications.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
As Supplied - DOWSIL™ 983 Structural Glazing Sealant Base			
	Color		White
	Physical Form		Paste
ASTM D1475	Specific Gravity		1.36
ASTM C1183	Extrusion Rate, 90 psi, 1/8"	g/min	300
	Orifice		
	VOC Content ²	g/l	< 4

1. ASTM: American Society for Testing and Materials.
2. Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds.

Typical Properties (Cont.)

Test	Property	Unit	Result
As Supplied - DOWSIL™ 983 Structural Glazing Sealant Curing Agent Black			
	Color		Black
	Physical Form		Paste
ASTM D1475	Specific Gravity		1.07
	VOC Content	g/l	< 150
As Supplied - DOWSIL™ 983 Structural Glazing Sealant Curing Agent Gray			
	Color		Dark gray
	Physical Form		Viscous liquid
ASTM D1475	Specific Gravity		1.02
	VOC Content		< 130
As Catalyzed - Mixed at 9:1 Base to Curing Agent by Volume (9:1 Volume = 12:1 Weight)			
	Snap Time	minutes	20–60
	Unit Handling Time, at 24°C (75°F), Minimum ³	hours ⁴	4–24 ⁴
	VOC Content ⁵	g/l	< 20
ASTM D2202	Flow/Sag (Slump)	mm (inches)	< 2.5 (< 0.1)
As Cured - 7 Days at 25°C (77°F) and 50% Relative Humidity			
ASTM C661	Durometer Hardness, Shore A	points	35–45
ASTM D412	Tensile Strength (Ultimate)	MPa (psi)	2.0 (300)
ASTM D412	Elongation (Ultimate)	%	400
ASTM D624	Tear Strength, Die B	N/m (ppi)	7,000 (40)
ASTM C794	Adhesion-in-Peel, Peel Strength	N/m (ppi)	5,600 (32)
ASTM C719	Movement Capability	%	±25
As Cured – 21 Days at 25°C (77°F) and 50% Relative Humidity			
ASTM C1135	Tensile Strength (at 10%)	Mpa (psi)	0.2 (30)
ASTM C1135	Tensile Strength (Ultimate)	Mpa (psi)	1.1 (160)
ASTM C1135	Elongation (Ultimate)	%	200
Specifications			
ASTM C1184	Structural Glazing Spec		Passes

3. Adhesion must be confirmed prior to shipping to job site.
4. Timeframe depends on how units are moved and verified for performance by deglazing for adhesion and fill.
5. Depending on mixing ratio.

Description

Mixed DOWSIL™ 983 Structural Glazing Sealant is a two-part silicone formulation. As supplied, the base is a smooth, white paste and the curing agent is a dark gray paste. Once catalyzed, the material cures to a high-modulus, flexible silicone rubber that is suitable for use in structural and weatherseal applications.

DOWSIL™ 983 Structural Glazing Sealant features excellent adhesion to most common construction materials, a physical property profile that is more than sufficient for structural adhesive and weatherseal applications, a non-corrosive by-product, and excellent weatherability, durability and recovery after repeated extension and compression up to 25%.

DOWSIL™ 983 Structural Glazing Sealant is compatible with reflective glass, laminated glass and most insulating glass. It can be used in deep narrow joints to obtain a full and complete cure.

How to Use

When DOWSIL™ 983 Structural Glazing Sealant is used in structural applications, the structural joint design MUST be reviewed by a technical service specialist.

Complete design and installation guidelines are contained in the Technical Manual, and must be followed for warranty applications when using this product.

Method of Application

DOWSIL™ 983 Structural Glazing Sealant Curing Agent must be thoroughly mixed into the base using an airless mixing system. DOWSIL™ 983 Structural Glazing Sealant is compatible with existing commercial, two-part silicone dispensing equipment. Neither hand mixing nor mechanical mixing is satisfactory due to incorporation of air, resulting in altered physical properties.

Lot matching of DOWSIL™ 983 Structural Glazing Sealant Curing Agent and Base is NOT required.

DOWSIL™ 983 Structural Glazing Sealant Curing Agent should be lightly stirred if any separation is seen prior to use. Because of its reactivity with atmospheric moisture, curing agent should not be exposed to air for prolonged periods.

DOWSIL™ 983 Structural Glazing Sealant is supplied as two separate components. As a custom feature, the cure rate may be adjusted by changing the base-to-curing-agent ratio from 8:1 to 10:1 by volume. Sealant physical properties are not significantly changed over this range. Changes in the temperature and humidity and material temperatures in the package will affect snap time and cure properties. Colder temperatures will slow cure and adhesion development. To obtain optimum adhesion, joints should be tooled immediately after sealant application to ensure complete substrate contact.

Questions about the use of DOWSIL™ 983 Structural Glazing Sealant can be answered by calling your local application sales engineer. Our laboratory personnel and technical service staff are also available for assistance.



**Handling
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

**Usable Life and
Storage**

DOWSIL™ 983 Structural Glazing Sealant should be stored in airtight, closed containers. When stored at or below 30°C (86°F) -base, 27°C (80°F) -curing agent, both the base and curing agent have a shelf life of 12 months from date of manufacture. Refer to product packaging for "Use By" date.

**Packaging
Information**

DOWSIL™ 983 Structural Glazing Sealant Curing Agent and DOWSIL™ 983 Structural Glazing Sealant Base are packaged separately.

DOWSIL™ 983 Structural Glazing Sealant Base is available in 250 kg (net weight) straight-sided drum.

DOWSIL™ 983 Structural Glazing Sealant Curing Agent is available in 19 kg (net weight) pail for black or 18 kg (net weight) for gray.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and
Environmental
Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

**Disposal
Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product
Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



©™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow
DOWSIL™ 983 Structural Glazing Sealant
© 2018–2024 The Dow Chemical Company. All rights reserved.